

HIGH TEMPERATURE WIRES AND CABLES FOR THE GENERAL MARKET SECTION I: CROSS LINKED ELASTOMERS

VARPREN INSULATED WIRES AND CABLES

VARPREN® 125 UL

Class B lead wires

UL and cUL approval



Approvals - standards

- UL approval as per standard UL 758-File no.: E101965.
- cUL approval (CSA) as per standard C22.2 No. 210-File no.: E101965.
- "FT2 flame rating" as per cUL approval.
- Halogen-free: IEC 60754-1 / EN 60754-1.

Applications

- Class B cabling for electric motors.
 - Lights.
- Industrial cabling in hot atmospheres up to +125 °C.

Options

- Nickel-plated copper core: contact us.
 - Other colours: contact us.
- Other nominal cross-sections: contact us.
- Other style nos. available: style 1505.
 - Other options: contact us.

Characteristics General

- Continuous operating temperatures: -30 °C to +125 °C.
- Good resistance to common chemical influences and impregnating varnishes.

Electrical

- Rated voltage: as per style no.
- Test voltage: 10 x Rated voltage.

Standard products

- Standard insulation colours: white, black, blue, brown, red or yellow/green.

		Style no.	3266		3173		3271	
		Approval	125 °C - 300 V		125 °C - 600 V		125 °C - 600 V	
Nominal cross-section	Nominal stranding		Avg thick-ness of insulation (mm)	Nominal diameter* (mm)	Avg thick-ness of insulation (mm)	Nominal diameter* (mm)	Avg thick-ness of insulation (mm)	Nominal diameter* (mm)
AWG	(mm²)							
24	0.22	7 x 0.20	0.38	1.45	0.76	2.3	0.76	2.3
-	0.25	8 x 0.20	0.38	1.5	0.76	2.3	0.76	2.3
22	0.34	19 x 0.15	0.38	1.6	0.76	2.35	0.76	2.35
-	0.5	19 x 0.18	0.38	1.7	0.76	2.5	0.76	2.5
20	0.6	19 x 0.20	0.38	1.75	0.76	2.6	0.76	2.6
-	0.75	24 x 0.20	0.38	1.9	0.76	2.7	0.76	2.7
18	0.93	19 x 0.25	0.38	2.05	0.76	2.8	0.76	2.8
-	1	32 x 0.20	0.38	2.15	0.76	2.9	0.76	2.9
16	1.34	19 x 0.30	0.38	2.35	0.76	3.1	0.76	3.1
-	1.5	30 x 0.25	0.38	2.45	0.76	3.15	0.76	3.15
14	-	19 x 0.37	0.38	2.7	0.76	3.4	0.76	3.4
-	2.5	50 x 0.25	0.38	2.85	0.76	3.6	0.76	3.6
12	-	37 x 0.34	0.38	3.2	0.76	4.0	0.76	4.0
-	4	52 x 0.30	0.38	3.3	0.76	4.1	0.76	4.1
10	-	37 x 0.43	0.38	3.9	0.76	4.7	0.76	4.7
-	6	84 x 0.30	0.38	4.0	0.76	4.8	0.76	4.8
8	-	70 x 0.40	-	-	-	-	1.14	6.3
-	10	77 x 0.40	-	-	-	-	1.14	7.0
6	-	105 x 0.40	-	-	-	-	1.14	7.8
-	16	119 x 0.40	-	-	-	-	1.14	8.4
4	-	168 x 0.40	-	-	-	-	1.14	9.2
-	25	196 x 0.40	-	-	-	-	1.14	10.0
2	35	259 x 0.40	-	-	-	-	1.14	11.3
1	-	342 x 0.40	-	-	-	-	1.40	12.4
-	50	370 x 0.40	-	-	-	-	1.40	12.9
1/0	-	425 x 0.40	-	-	-	-	1.40	13.6
2/0	70	340 x 0.50	-	-	-	-	1.40	14.8
3/0	-	434 x 0.50	-	-	-	-	1.40	16.3
-	95	475 x 0.50	-	-	-	-	1.40	17.1
4/0	-	546 x 0.50	-	-	-	-	1.40	18.0
Conducting metal			BCDEFG		BCDEFG		BCDEFG	

For this product, please contact:

OMERIN division principale

Zone Industrielle - F 63600 Ambert
Tel. +33 (0)4 73 82 50 00 - Fax +33 (0)4 73 82 50 10
omerin@omerin.com

Omerin division silişol

BP 87 - ZI du Devey - F 42000 Saint-Etienne
Tel. +33 (0)4 77 81 36 00 - Fax +33 (0)4 77 81 37 00
silişol@omerin.com

KEY

Conducting metals
B Tin-plated copper
B* Tin-plated copper (ø > 0.38 mm)
C Nickel-plated copper
D Silver-plated copper
E Nickel
F Bare copper
F* Bare copper (ø > 0.38 mm)
G Nickel-plated copper 27 %

AWM I A Internal wiring, not subject to mechanical abuse
AWM I A/B Internal wiring
AWM II A/B External or internal wiring

NS Not Specified
VNS Voltage Not Specified

■: UL approved nominal cross-sections only.

* The diameter is provided for information purposes as it may vary depending on the stranding of the core. Only the average thickness of insulation should be taken into account.